

### NORSOK M-501 Coating System No.1 (Shall be pre-qualified)

Carbon steel with maximum operating temperature < 120°C

- Structural steel
- Exteriors of equipment, vessels, piping and valves (not insulated)

Product Name	General Name	DFT	Certificate No.
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	N960298A
ECOMAX SH-HB	Epoxy intermeidiante coat	170	
UNY MARINE HS	Polyurethane topcoat	50	
<b>Total</b>		<b>280</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	LAB15-0152-REP
ECOMAX SH-HB	Epoxy intermeidiante coat	220	
ECOMAX SH-HB	Epoxy paint	220	
<b>Total</b>		<b>500</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	2014-5076-rev.01
BANNOH 500	Epoxy intermeidiante coat	100	
UNY MARINE HS	Polyurethane topcoat	40	
<b>Total</b>		<b>200</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	N964257
ECOMAX SH-HB	Epoxy intermeidiante coat	190	
FLUOREX FINISH	Fluorocarbon topcoat	30	
<b>Total</b>		<b>280</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	N969971
BANNOH 4000	Epoxy intermeidiante coat	170	
UNY MARINE HS	Polyurethane topcoat	50	
<b>Total</b>		<b>280</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	N969972
BANNOH 4000	Epoxy intermeidiante coat	170	
UNY MARINE HS	Polyurethane topcoat	50	
<b>Total</b>		<b>280</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	N969973
BANNOH 3000	Epoxy intermeidiante coat	170	
UNY MARINE HS	Polyurethane topcoat	50	
<b>Total</b>		<b>280</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	N969974
BANNOH 3000	Epoxy intermeidiante coat	170	
UNY MARINE HS	Polyurethane topcoat	50	
<b>Total</b>		<b>280</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	N969975
BANNOH 2000	Epoxy intermeidiante coat	170	
UNY MARINE HS	Polyurethane topcoat	50	
<b>Total</b>		<b>280</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	LAB16-0275-REP S5
ECOMAX SH-HB	Epoxy intermeidiante coat	170	
UNY MARINE HS	Polyurethane topcoat	50	
<b>Total</b>		<b>280</b>	

**CHUGOKU MARINE PAINTS,LTD.**

( <http://www.cmp.co.jp/> )

All products supplied and technical advice or recommendations given are subject to our standard condition of Sales.



### NORSOK M-501 Coating System No.2A

Sealer for thermally sprayed aluminium or alloys of aluminium < 120°C

Product Name	General Name	DFT	Certificate No.
EPICON A-100 PRIMER	Epoxy sealer coat	-	
<b>Total</b>		-	

### NORSOK M-501 Coating System No.2A

Sealer for thermally sprayed aluminium or alloys of aluminium > 120°C

Product Name	General Name	DFT	Certificate No.
SILICON HR SILVER	Silicone sealer coat	-	
<b>Total</b>		-	

### NORSOK M-501 Coating System No.2B

Sealer for thermally sprayed zinc or alloys of zinc

Product Name	General Name	DFT	Certificate No.
GALVANITE No.400 PRIMER	Tie coat	-	
BANNOH 500	Epoxy intermediate coat	125	
UNY MARINE HS	Polyurethane topcoat	75	
<b>Total</b>		200	
GALVANITE No.400 PRIMER	Tie coat	-	
BANNOH 500	Epoxy intermediate coat	125	
EPICON FINISH HB	Epoxy topcoat	75	
<b>Total</b>		200	
GALVANITE No.400 PRIMER	Tie coat	-	
BANNOH 500 AC	Epoxy intermediate coat	125	
UNY MARINE HS	Polyurethane topcoat	75	
<b>Total</b>		200	
GALVANITE No.400 PRIMER	Tie coat	-	
BANNOH 3000	Epoxy intermediate coat	125	
UNY MARINE HS	Polyurethane topcoat	75	
<b>Total</b>		200	
GALVANITE No.400 PRIMER	Tie coat	-	
BANNOH 4000	Epoxy intermediate coat	125	
UNY MARINE HS	Polyurethane topcoat	75	
<b>Total</b>		200	

### NORSOK M-501 Coating System No.3A

Potable water tanks

Product Name	General Name	DFT	Certificate No.
CLEANKEEP 5000 HOLDING	Epoxy holding primer	50	LAB11-0357-REP
CLEANKEEP 5000	Solvent-free epoxy	250	
<b>Total</b>		<b>300</b>	
CLEANKEEP 5000	Solvent-free epoxy	300	
<b>Total</b>		<b>300</b>	
CLEANKEEP 5500	Solvent-free epoxy	300	
<b>Total</b>		<b>300</b>	

### NORSOK M-501 Coating System No.3B (Shall be pre-qualified)

Ballast water tanks / internal seawater filled compartments

Product Name	General Name	DFT	Certificate No.
BANNOH 500AC	Epoxy primer	160	N960320
BANNOH 500AC	Epoxy primer	160	
<b>Total</b>		<b>320</b>	
CMP NOVA 2000	Epoxy primer	160	16MLVW7-21
CMP NOVA WE-100	Epoxy primer	300	
CMP NOVA 2000	Epoxy primer	160	
<b>Total</b>		<b>620</b>	
BANNOH 500	Epoxy primer	160	PSPC
BANNOH 500	Epoxy primer	160	
<b>Total</b>		<b>320</b>	
BANNOH 1500	Epoxy primer	160	PSPC
BANNOH 1500	Epoxy primer	160	
<b>Total</b>		<b>320</b>	
BANNOH 2000	Epoxy primer	160	PSPC
BANNOH 2000	Epoxy primer	160	
<b>Total</b>		<b>320</b>	
BANNOH 3000	Epoxy primer	160	JP130705
BANNOH 3000	Epoxy primer	160	
<b>Total</b>		<b>320</b>	
BANNOH 4000	Epoxy primer	160	JP130707
BANNOH 4000	Epoxy primer	160	
<b>Total</b>		<b>320</b>	
CMP NOVA 2000	Epoxy primer	160	PSPC
CMP NOVA 2000	Epoxy primer	160	
<b>Total</b>		<b>320</b>	
CMP NOVA 2000 E	Epoxy primer	160	PSPC
CMP NOVA 2000 E	Epoxy primer	160	
<b>Total</b>		<b>320</b>	

**CHUGOKU MARINE PAINTS, LTD.**

( <http://www.cmp.co.jp/> )

All products supplied and technical advice or recommendations given are subject to our standard condition of Sales.

### NORSOK M-501 Coating System No.3C

Tank for stabilised crude, diesel and condensate

Product Name	General Name	DFT	Certificate No.
EPICON T-800	Epoxy Phenolic	100	LAB11-0360-REP
EPICON T-800	Epoxy Phenolic	100	
EPICON T-800	Epoxy Phenolic	100	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS	Epoxy Phenolic	150	
EPICON T-800 HS	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	

### NORSOK M-501 Coating System No.3D

Process vessels < 0.3MPa < 75°C

Product Name	General Name	DFT	Certificate No.
EPICON T-800	Epoxy Phenolic	100	Report-2015-5090- Nafta-test-for-CMP- rev-00
EPICON T-800	Epoxy Phenolic	100	
EPICON T-800	Epoxy Phenolic	100	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS	Epoxy Phenolic	150	
EPICON T-800 HS	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	

### NORSOK M-501 Coating System No.3E

Process vessels < 7.0MPa < 80°C

Product Name	General Name	DFT	Certificate No.
EPICON T-800	Epoxy Phenolic	100	Report-2015-5090- Nafta-test-for-CMP- rev-00
EPICON T-800	Epoxy Phenolic	100	
EPICON T-800	Epoxy Phenolic	100	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS	Epoxy Phenolic	150	
EPICON T-800 HS	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	

**CHUGOKU MARINE PAINTS, LTD.**

( <http://www.cmp.co.jp/> )

All products supplied and technical advice or recommendations given are subject to our standard condition of Sales.

### NORSOK M-501 Coating System No.3F

Process vessels < 3.0MPa < 130°C

Product Name	General Name	DFT	Certificate No.
EPICON T-800	Epoxy Phenolic	100	Report-2015-5090- Nafta-test-for-CMP- rev-00
EPICON T-800	Epoxy Phenolic	100	
EPICON T-800	Epoxy Phenolic	100	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS	Epoxy Phenolic	150	
EPICON T-800 HS	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	

### NORSOK M-501 Coating System No.3G

Vessels for storage of methanol, mono ethyl glycol etc.

Product Name	General Name	DFT	Certificate No.
GALBON S-HB	Zinc ethyl silicate	75	LAB11-0359-REP
<b>Total</b>		<b>75</b>	

**NORSOK M-501 Coating System No.4 (Shall be pre-qualified)**

Non skid epoxy screed

Product Name	General Name	DFT	Certificate No.
CMP NOVA WE-100	Epoxy paint	3000	16MLVW7-23
		<b>Total 3000</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	N960298A
ECOMAX SH-HB	Epoxy intermediate coat (With Non-skid aggregate)	-	
UNY MARINE HS	Polyurethane topcoat	50	
		<b>Total</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	184Y3A1-2
BANNOH 500	Epoxy intermediate coat (With Non-skid aggregate)	-	
UNY MARINE HS	Polyurethane topcoat	50	
		<b>Total</b>	

### NORSOK M-501 Coating System No.5A (Shall be pre-qualified)

Epoxy based fire protection

Product Name	General Name	DFT	Certificate No.
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	LAB-15-0169-REP
EPICON UNDERCOAT HB	Epoxy tie coat	25	
Charrex PFP-1000	Epoxy based fire protection	6000	
<b>Total</b>		-	
BANNOH 500	Epoxy primer	50	LAB16-0615-REP S1
Charrex PFP-1000	Epoxy based fire protection	6000	
<b>Total</b>		-	
BANNOH 500AC	Epoxy primer	50	LAB16-0616-REP S2
Charrex PFP-1000	Epoxy based fire protection	6000	
<b>Total</b>		-	
BANNOH 4000	Epoxy primer	50	LAB16-0617-REP S3
Charrex PFP-1000	Epoxy based fire protection	6000	
<b>Total</b>		-	
BANNOH 4000	Epoxy primer	50	LAB16-0618-REP S4
Charrex PFP-1000	Epoxy based fire protection	6000	
<b>Total</b>		-	
UNIVAN NT	Epoxy primer	50	LAB16-0619-REP S5
Charrex PFP-1000	Epoxy based fire protection	6000	
<b>Total</b>		-	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	60	LAB16-0620-REP S6
Charrex PFP-1000	Epoxy based fire protection	6000	
<b>Total</b>		-	



### NORSOK M-501 Coating System No.6A

Un-insulated stainless steel

Product Name	General Name	DFT	Certificate No.
EPICON S-100 PRIMER	Epoxy primer for stainless	30	LAB11-0351-REP
EPICON UNDERCOAT HB	Epoxy intermediate coat	120	
UNY MARINE HS	Polyurethane topcoat	75	
<b>Total</b>		<b>225</b>	

### NORSOK M-501 Coating System No.6A

Un-insulated Aluminium

Product Name	General Name	DFT	Certificate No.
EPICON A-100 PRIMER	Epoxy primer for stainless	30	
EPICON UNDERCOAT HB	Epoxy intermediate coat	100	
UNY MARINE HS	Polyurethane topcoat	75	
<b>Total</b>		<b>205</b>	

### NORSOK M-501 Coating System No.6B

Hot dipped galvanised steel

Product Name	General Name	DFT	Certificate No.
GALVANITE No.400 PRIMER	Epoxy primer for galvanised	50	LAB13-0549-REP
EPICON UNDERCOAT HB	Epoxy intermediate coat	100	
UNY MARINE HS	Polyurethane topcoat	75	
<b>Total</b>		<b>225</b>	

### NORSOK M-501 Coating System No.6C

Insulated stainless steel piping and vessels < 150°C

Product Name	General Name	DFT	Certificate No.
EPICON T-800 HS-GF	Epoxy Phenolic	125	LAB11-0352-REP
EPICON T-800 HS-GF	Epoxy Phenolic	125	
<b>Total</b>		<b>250</b>	

### Coating System No.7A (Shall be pre-qualified)

NORSOK M-501 Carbon and stainless steel in the splash zone

Product Name	General Name	DFT	Certificate No.
BANNOH 500 AC	Epoxy primer	150	LAB14-0291-REP
ECOMAX SH-HB	Epoxy paint	450	
<b>Total</b>		<b>600</b>	
PERMASTAR WE200 U/C	Epoxy primer	150	2014-5080, Rev. 01
PERMASTAR WE200 FINISH	Epoxy paint	450	
<b>Total</b>		<b>600</b>	
EPICON ZINC HB-2 SH	Zinc rich epoxy primer	150	LAB15-0152-REP
ECOMAX SH-HB	Epoxy intermeidiatae coat	175	
ECOMAX SH-HB	Epoxy paint	175	
<b>Total</b>		<b>500</b>	
BANNOH 3000	Epoxy primer	200	N969984
BANNOH 3000	Epoxy primer	200	
BANNOH 3000	Epoxy primer	200	
<b>Total</b>		<b>600</b>	
PERMAX NO.3300	Epoxy glass flake	300	LAB16-0278-REP
PERMAX NO.3300	Epoxy glass flake	300	
<b>Total</b>		<b>600</b>	
BANNOH 500 AC	Epoxy primer	150	MAN229389-001
PERMAX NO.3300	Epoxy glass flake	450	
<b>Total</b>		<b>600</b>	
BANNOH 3000	Epoxy primer	150	MAN229390-001
PERMAX NO.3300	Epoxy glass flake	450	
<b>Total</b>		<b>600</b>	

### NORSOK M-501 Coating System No.7B (Shall be pre-qualified)

Submerged carbon and stainless steel < 50°C

Product Name	General Name	DFT	Certificate No.
BANNOH 500AC	Epoxy primer	100	N960323
PERMAX No.3300	Epoxy glass flake	250	
<b>Total</b>		<b>350</b>	
BANNOH 500AC	Epoxy primer	160	N960322
BANNOH 500AC	Epoxy primer	160	
<b>Total</b>		<b>320</b>	
BANNOH 4000	Epoxy primer	175	N964254
BANNOH 4000	Epoxy primer	175	
<b>Total</b>		<b>350</b>	
PERMASTAR WE 300 U/C	Epoxy paint for underwater	450	2014-5068
PERMASTAR WE 300 FINISH	Epoxy paint for underwater	600	
<b>Total</b>		<b>1050</b>	
BANNOH 500AC	Epoxy primer	150	LAB13-0541-REP
BANNOH 500AC	Epoxy primer	175	
BANNOH 500AC	Epoxy primer	175	
<b>Total</b>		<b>500</b>	
ECOMAX ZINC PRIMER	Zinc rich epoxy primer	20	LAB14-0292-REP
PERMAX NO.3000S	Epoxy glass flake	490	
PERMAX NO.3000S	Epoxy glass flake	490	
<b>Total</b>		<b>1000</b>	
BANNOH 3000	Epoxy primer	175	LAB16-0279-REP
BANNOH 3000	Epoxy primer	175	
<b>Total</b>		<b>350</b>	
BANNOH FS AL	Epoxy primer	175	MAN229391-001
BANNOH FS AL	Epoxy primer	175	
<b>Total</b>		<b>350</b>	

**NORSOK M-501 Coating System No.8**

Structural carbon steel with maximum operating temperature < 80°C in internal and fully dry and ventilated area.

Product Name	General Name	DFT	Certificate No.
BANNOH 500	Epoxy primer	150	
		<b>Total 150</b>	
BANNOH 2000	Epoxy primer	150	
		<b>Total 150</b>	
EPICON ZINC HB-2	Zinc rich epoxy primer	60	
EPICON PRIMER HB	Epoxy Primer	25	
		<b>Total 85</b>	

**NORSOK M-501 Coating System No.9**

Bulk supplied carbon steel valves with maximum operating temperature up to 150°C.

Product Name	General Name	DFT	Certificate No.
EPICON T-800	Epoxy Phenolic	100	
EPICON T-800	Epoxy Phenolic	100	
EPICON T-800	Epoxy Phenolic	100	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS	Epoxy Phenolic	150	
EPICON T-800 HS	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
EPICON T-800 HS-GF	Epoxy Phenolic	150	
<b>Total</b>		<b>300</b>	